

# REOLOSIL<sup>®</sup>

RD-T-17-01-02

## QS-09

### Hydrophilic Fumed Silica

*REOLOSIL QS-09 is a very fine amorphous silicon dioxide made by combustion of high purity silicon tetrachloride with oxygen and hydrogen.*

*It is used as reinforcing, thickening, anti-settling, grinding, and free flow agent.*

#### Typical Properties

Specific Surface Area (BET)	70-110 m <sup>2</sup> /g
Bulk Density	50 g/L (approximately)
pH (4% suspension)	4.2
SiO <sub>2</sub> purity (Dry basis)	> 99.9 %
Cl	< 50 ppm
Al	< 20 ppm
Fe	< 20 ppm
44μm Residue	< 0.01 %
Moisture Content (Dry up, %) *1	< 1.0 %

The data represents typical values (no product specification).

\*1 When leaving plant

#### Characteristic Properties

*Small specific surface area (mean primary particle size: ca.22nm) .*

#### Typical Packaging Forms

*Packaged in 10 kg / paper bag.*

The recommendations and suggestions given in this literature are made without any representation or warranty as they are presented for your own investigation and verification. The Products discussed are sold without warranty, expressed or implied. Statements concerning specific applications of our products or the processes described should not be construed as permission or recommendation to use the same in a manner that infringes upon any patent, or to use a patented invention without license. Before use, refer to the Safety Data Sheet (SDS) for these products for important safety information.